

The test results within this specification have been taken from random samples during new production operations. No 3rd party testing has been performed so these results should be seen as a guide only.

Product Specification – Technical (SAMPLE TESTING)

PRODUCT NAME: CUSTOM CUSHION

CODE: 24046

GENERAL

	PROPERTY		SPECIFICATION
G1	Length	m	10.0
G2	Width	m	1.8
G3	Area	m ²	18
G4	Density	kg/m ³	120 ± 10%
G5	Roll weight incl. packaging	kg	24.3 ± 2
G6	Colour Foam		Various
G7	Backing		Laminate of blue colour
G8	Packaging		Clear plastic with sticker

TECHNICAL

	PROPERTY		REQ. PER AS4288 – 1999	TYPICAL RESULT	TEST METHOD
T1	Thickness	mm	± 12%	11.0 NOMINAL	AS 2111.1
T6	Work of Compression (WOC) after dynamic loading (1000 impacts)	J/m ²	120 min 200 max	COMPLIES	AS 4288 – 2003
T7	Retention of WOC after dynamic loading	%	40 min	COMPLIES	AS 4288 – 2003
T8	Deflection @ 100 KPa after dynamic loading (1000 impacts)	mm	4.5 min 9.0 max	COMPLIES	AS 4288 – 2003

AIRSTEP CUSTOM CUSHION foam underlay is made in Dandenong Australia from recycled polyurethane foam. The underlay is produced by crumbing and binding the foam into a cylindrical log. This log is then peeled and laminated into a continuous sheet. **CUSTOM CUSHION** is classed as a **luxury underlay**, all edges are square trimmed and the underlay is to be free of holes and inclusions.

The packaging is a heat sealed polyethylene wrap and end sealed with a metal clip.

CONTROLLED DOCUMENT - SUBJECT TO REVISION

Information contained in uncontrolled or photocopied material may be superseded without notice.

Doc No:	QS CUSTOM CUSH. (AS)	Originator:	J Ross	Date:	18/05/21	Q.A. Officer:	J Ross
Issue No:	1	Approved:	P Verschaeren	Date:	18/05/21	Page 1 of 1	